



Article Gate T3777

Method of Production	tufted
Polmaterial	100 % polyamide
Loops per unit area approx.	164.000 /m ²
Dyeing	Piece dyeing
Backsizing	Synthetics
Backing	Textile back
Pile weight approx.	1.300 g/m ²
Total weight approx.	2.450 g/m ²
Pile height approx.	7 mm
Total height approx.	10 mm
Delivery width	400 cm
Repeat length	
Repeat width	
Qualification	CE 23 JAB Teppiche HEINZ ANSTOETZ KG Dammheider Str. 67 D-32052 Herford-Elverdissen EN 1307 JT-WM33-023-03 EN 14041:2018-05 Notified Body: 2401 Floor covering to be used within a building * In the glued state, tested with Uzin UZ 57
Color fastness / light fastness	ISO 105-B02: 5-6
Abrasion resistance wet / dry	ISO 105-X12: 4
Water fastness	ISO 105-E01: 4-5
Fastness to seawater	
Fastness to chlorine water	
resistance to heat conduction	ISO 8302 : 0,12 m ² /KW
Standard of flammability	EN 13501-01 Cfl-s1 In the glued state, tested with Uzin UZ 57
Absorption of step sound	EN ISO 140-8: 32 dB
Sound absorption coefficient	α_w 0,20
Moth protection	

We reserve the right to make any technical changes which serve to improve the products.

Version: 31.05.2023